

Dhr. Chris Heynen
HEYNEN SYSTEMS BV
Staalstraat 31
NL-8211 AH LELYSTAD
NEDERLAND

your delivery of
2008-05-29

your reference

our reference
PVH/10717

date
Zwijnaarde, 2008-11-24

Analysis Report 63346/L

Required tests :

Determination of the abrasion resistance of a woven fabric - Martindale

| Identification number | Information given by the client | Date of receipt |
|------------------------------|--|------------------------|
| T805813 | Circular knitting, 100% polyamide yarn, 78dtex, 16 gauge | 2008-06-02 |

Pros Van Hoeyland
order responsible

For further information, please contact our sectorial adviser Pros Van Hoeyland

This report runs to 2 pages and may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel. The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.

VAT BE 0459.218.289
CENTEXBEL-GENT
Technologiepark 7
BE-9052 Zwijnaarde
Tel. + 32 9 220 41 51 • Fax + 32 9 220 49 55
e-mail gent@centexbel.be

Fin. Acc. 210-0472965-45

IBAN BE44 2100 4729 6545

CENTEXBEL-BRUSSELS
Montoyerstraat 24 B2
BE-1000 Brussels
Tel. + 32 2 287 08 30 • Fax + 32 2 230 68 15

Reference : T805813 - Circular knitting, 100%polyamide yarn, 78dtex, 16 gauge

Determination of the abrasion resistance of a woven fabric - Martindale

1. Method:

Applied standard : EN ISO 12947 part 2 (year: 1998)
on conditioned material (20°C and 65% rel. hum.)

Deviations of the standard : - between the tested sample and the PUR foam was the reference abradant placed.
- the sample is (slightly) stretched for fixing into the holder

Apparatus : Martindale Abrasion Machine

Pressure on test specimen : 12 kPa

Reference abradant : crossbred worsted spun, plain woven fabric

Type of the felt : woven felt

Number of test specimens : 4 circular test specimens to the end point

2. Results:

Date of ending the test: 21-11-2008

Physically significant end point: a hole into the knitting

| specimen | number of rubs at which specimen breakdown occurs |
|----------|---|
| 1 | 100 000 |
| 2 | >100 000 |
| 3 | >100 000 |
| 4 | >100 000 |
| mean | - |

See test specimens enclosed.