

TÜV Rheinland LGA Products GmbH · 51101 Cologne

Heynen Systems BV
Chris Heynen
Staalstraat 31
8211 AH Lelystad
NETHERLANDS

Contact
E-mail
Phone
Fax
Cologne,

Petra Van Dyck
Petra.Van.Dyck@de.tuv.com
+49 221/806-2129
+49 221/806-1464
01.03.2012

Report No. 0003044523/30 AZ110529

Test item: One sample of fabric

Identification: Tricover, white, 100% PA code: 9101150008/02

Condition at delivery: No claim

Date of delivery: 22.02.2012

Place of testing: Cologne


Test period: 24.02.2012 to 01.03.2012


Test scope: Parameters selected by customer

Test specification: IKEA IOS-MAT-0010 Vers. AA-10911-10 dated 2011-05-13

Test result: Pass - According to the kind and extent of tests performed the test item meets the test specification.

Cologne, 01.03.2012


Dipl.-Ing. Gunther Bier
(Expert)


Petra Van Dyck
(Expert)

The test results exclusively refer to the samples examined.

This report shall not be reproduced except in full without written approval and does not authorize the use of a TÜV Rheinland Group label.

TÜV Rheinland LGA Products GmbH, Tillystr. 2, D-90431 Nuremberg, Tel +49 911 655 5225, Fax +49 911 655 5226, Mail service@de.tuv.com, Web www.tuv.com
Board of Management: Dipl.-Ing. Jörg Mähler, Dipl.-Kfm. Dr. Jörg Schlösser, Amtsgericht Nürnberg HRB 26013, VAT-No: DE811835490

Report No.: 0003044523/30 AZ110529

Date: 01.03.2012

2. Results

Formaldehyde, textile extraction method

Sample No.	110529-002		
Sample composition	Art. 1 Tricover, white, 100% PA code: 9101150008/02		
Unit	ppm		
Formaldehyde	<10		

Limit value for materials without reference in TED 300 ppm

Organotin compounds

Sample No.	110529-001		
Sample composition	Art. 1 Tricover, white, 100% PA code: 9101150008/02		
Unit	mg/kg		
Organotin compounds, total			
Monobutyltin, MBT	<0,005		
Dibutyltin, DBT	<0,005		
Tributyltin, TBT	<0,005		
Tetrabutyltin, TeBT	<0,005		
Monooctyltin, MOT	<0,005		
Diocetyl tin, DOT	<0,005		
Tricyclohexyltin, TcyT	<0,005		
Triphenyltin, TPHT	<0,005		

Limit values:

DBT and TBT 0,1 mg/kg each

Sum of all organotin compounds 2,5 mg/kg

----End of results----



Report No.: 0003044523/30 AZ110529

Date: 01.03.2012

3. Summary of methods

Formaldehyde, textile extraction method	Standard: DIN EN ISO 14184-1	Issue date: 01.12.11
--	-------------------------------------	-----------------------------

Method description:
 Textiles - Determination of formaldehyde - Part 1: Free and hydrolyzed formaldehyde (water extraction method), identical to BVL B 82.02-1 and Japanese LAW 112

Organotin compounds		
----------------------------	--	--

Method description:
 In-house method - Determination of organotin compounds after extraction with methanolic solvent and derivatisation. Quantification by GC-MS

Notes:
 Quantification equates the DIN EN ISO 17353.